

FF440 | Flowfast Pourable Repair Mortar

1

SURFACE PREPARATION

- Surfaces to be repaired must be clean, dry and free of any loose, friable material.
- Any suspect material within the repair area which may compromise the effectiveness of the repair but is too difficult to manually remove, can be knocked out with a hammer and chisel.
- A wire brush is effective for removing surface contamination followed by sweeping out the repair area.
- RizistalClean can be used as a degreaser if there are small areas of oil or grease contamination.

2

MIXING

- Flowfast is a two part product; a tin of liquid and a container of powder.
- Mix the two components within the powder container using a mixing paddle attached to a drill.
- The mixed material hardens rapidly so it is recommended that it is poured immediately.
- We recommend using safety glasses, gloves and coveralls throughout (available separately).

3

APPLICATION

- When a smooth even consistency is achieved, simply pour flowfast into the repair area and it will self level with minimal trowelling.
- To prevent streaks, wipe the blade with with Rizistal Safer Solvent.
- Foot traffic only areas can be feather edged, but edges are not recommended for medium or heavy trafficked areas.

For further information please contact the Support Team



FF440 | Flowfast Pourable Repair Mortar

4

WORKING TIME

The following approximate working times are for installing the product after mixing is complete but before the curing process affects your ability to move the material and smooth the surface. At this point the performance of the material will be adversely affected and should be discarded.

- Flowfast Pourable Repair Mortar: 10 minutes at 15°C - 20°C

5

CURING TIME

	Light Traffic	Heavy Traffic
Flowfast @ 20°C	1 Hour	4 Hours
Flowfast below 10°C	24 Hours	24 Hours

After installation, this product must be kept clean and dry for 12 to 18 hours, otherwise the product performance will be seriously affected, which may result in discolouration and lack of cure.

For further information please contact the Support Team

